



SAINT-GOBAIN

## abecote® 400 HB

### HI-BUILD EPOXY FLOOR COATING

#### DESCRIPTION

**abecote® 400 Hi-build** is an economical four-component, solvent-free epoxy flooring system comprising a clear resin and hardener, pre-packed filler and a ready-for-use pigment paste.


#### USES

Floor coating in ablution blocks, walkways, food processing plants, hospitals and schools etc. May also be used as a binder for abrasive grit to yield non-slip floor finishes.

#### ADVANTAGES

- Good protective qualities
- Good resistance to chemicals
- Reduces maintenance
- Range of colours
- Can be applied onto a variety of surfaces
- Seamless and hygienic

#### abecote® 400 Hi-build



#### PROPERTIES OF WET MATERIAL

Mixing ratio	See quantities under packaging for 7.1l Kit and Bulk Pack
Density	Resin: 1.084 kg/l Mix: 1.526 kg/l
Colours	Pale Grey G62 Medium Sea Grey G24 Drakensberg Green H36 Light Stone C37 Red Oxide Leaf Green (chrome oxide) Sand Yellow Other colours on application
Flash point	> 100 °C
Dilution	Do not dilute
Shelf life	2 years from date of manufacture and in sealed containers @ 25 °C

#### PROPERTIES DURING APPLICATION

Pot life	approximately 40 minutes (5 L mixed @ 25 °C)
Work Life	approximately 60 minutes (after spreading @ 25 °C)
Volume solids	100%
Curing time @ 25 °C	Touch: 8 hrs Light Foot traffic: 24 hrs Full cure: 7 days
Overcoating time @ 25 °C	Minimum: 12 hrs Maximum: 36 hrs
Application temperature range	> 15 °C & < 35 °C

Do not apply coating if humidity is in excess of 85% @ 21 °C or 75% @ 10 °C

Do not apply coating if the substrate temperature is at least 3 °C (5 °C is better) above dew point.

#### PHYSICAL PROPERTIES OF CURED FILM

Maximum service temperature	60 °C
Shrinkage after cure	Negligible
Weather resistance	Chalks on external exposure
Chemicals	Good resistance to water, oil, fats, greases, diesel, dilute acids and alkalis

#### SURFACE PREPARATION

##### Precautionary Notes

- (1) The substrate must be dry before application. For concrete, moisture content tests must be conducted prior to application of the priming system. Maximum moisture content should be between 4 - 5% (preferably a Protimeter Survey Master or equivalent, or Dynamic). Calcium Chloride moisture "weight gain" over 24 hours, or at least a practical overnight "plastic sheet test" is also advisable (approximately 1 m<sup>2</sup> masked down on surface).
- (2) Concrete substrate must have a minimum tensile strength of 1.5 N/mm<sup>2</sup>.

Concrete shall be free of all laitance and preferably should be lightly vacuum blast cleaned leaving a uniform texture. All blemishes in the surface such as pop-outs, omegas, blowholes and honeycomb should be patched with **epidermix® 201**. This should be left overnight to cure and shall then be rendered smooth.

For a smooth final finish, the surface profile, peak to valley, should not exceed 25% of the coating thickness. If the surface is very irregular, consideration should be given to the use of **abe® prime SL**, a solvent free epoxy self leveling primer.

## BONDING/PRIMING

If **abe® prime SL** is not used, then **abecote® Hi-build** is normally applied over a thoroughly sealed concrete surface using up to two coats of **abecote® 337**.

Over coating of the primer with **abecote® 400 Hi-build** should comply with the over coating time requirements laid down for the specific primer. The over coating time for **abecote® WD 337** is 4 - 6 hours.

## MIXING

### Precautionary Notes

- (1) When decanting base from bulk supply, thorough stirring must be accomplished beforehand.
- (2) In order to avoid colour variation in large expanses, one must ensure that the same pigment batch is used and is carefully and accurately dispensed (factory batching available on request).

Proper mixing and proportioning of the epoxy binder (base and activator), filler and pigment is essential for good results with no colour variation from mix to mix.

Transfer pre-measured volume of flooring base resin to mixer. Add pigment and activator and homogenize. Add filler slowly and mix well.

### NOTE:

- (1) A slow speed mixer must be used. Ensure that the mixing vanes are below the surface of the mix to minimize air entrapment. The stirrer mixing vane configuration should be such as not to introduce unwanted aeration. Also, for this type of mixing, transferring the base/activator combination to a new container i.e. "re-mixing" will eliminate contamination due to unmixed base which is inclined to cling to the walls of the original container.
- (2) Where light colours (yellows/white etc.) are used, the addition of 2 units of pigment pastes per kit is advised to ensure opacity. A similar coloured primer is also recommended.

COVERAGE		
Aggregate loading/5ℓ Resin		
	5 kg	7.5 kg
dft per coat	approximately 400 µm	approximately 1 000 µm
Theoretical coverage	17.7 m <sup>2</sup>	8.0 m <sup>2</sup>

## APPLICATION

### Precautionary Note

Prevailing weather conditions must be taken into account otherwise surface defects can occur (see under "properties during application").

**abecote® 400 Hi-build** should be applied by first pouring a bead of material in the form of a ribbon on the surface to be coated. Do not leave material in the container too long because it will set faster thus reducing the work life. Using a serrated trowel, spread the applied material at the specified rate. Apply as evenly as is possible, working from left to right, and then back. Approximately 10 minutes after application, roll using a porcupine roller to aid in excess air release.

All over-coating times must be strictly adhered to. **abecote® 400 Hi-build** will not cure if applied at below 10 °C.

## NON-SLIP SURFACE

### PRECAUTIONARY NOTE

Overcoat times of 48 hours maximum must be adhered to at all stages.

A non-slip surface can be achieved by applying a clear bond coat of **abecote® 400 Hi-build Resin** onto the relevant cured pigmented **abecote® 400 Hi-build System** base coat at an approximate rate of 3 m<sup>2</sup>/ℓ and broadcasting into this a suitable grit at the rate of approximately 50 g/m<sup>2</sup>. Ensure that grit application is evenly broadcast and back-rolled using a short mohair fibre roller.

Also see 'Non-slip floor finishes' literature.

## CLEANING OF EQUIPMENT

**abe® super brush cleaner** before setting.

## PROTECTION/MAINTENANCE ON COMPLETION

Enlist the services of experienced cleaning specialists. Furthermore, the following recommendation will go a long way to maintain the original appearance of the epoxy floor viz.

- (1) Protect from trafficked dirt/grit ingress into coated area by using dirt traps etc.
- (2) Use of a "renewable" clear high wear polymer based floor polish will reduce scratching and "black heel".
- (3) Encourage frequent maintenance cleaning.

## MODEL SPECIFICATION

The epoxy floor system will be **abecote® 400 Hi-build**, a four-component, solvent-free epoxy floor system comprising resin and hardener, filler and pigment paste applied in accordance with **a.b.e.®** recommendations.

## PACKAGING

SMALL PACK	
Resin: Base and Activator 5 L (Kit) (40001-005)	
<b>Hi-build</b> aggregate 5 kg (20052-005) for 1000 µm dft	5 kg (yield 7.1 L)
<b>Hi-build</b> aggregate 7.5 kg (20052-075) for 1000 µm dft	7 kg (yield 8 L)
Pigment paste (200xy-350) approximate density 1.9 kg/L	1 x 0.35 kg
BULK PACK	
Resin system comprises	
Base (40005-025)	2 x 25ℓ
Activator (40010-025)	1 x 25ℓ
<b>Hi-build</b> aggregate 5 kg (20052-005) for 1000 µm dft	15 x 5 kg (yield 106.5ℓ)
<b>Hi-build</b> aggregate 7.5 kg (20052-075) for 1000 µm dft	15 x 7.5 kg (yield 120ℓ)
Pigment paste (200-xy-350) approximate density 1.9 kg/L	0.35 kg

**abe®** white non slip aggregate grit 60#

**abe®** white non slip aggregate grit 100#

## HANDLING & STORAGE

All **abecote® 400 Hi-build** related products have a shelf life of 2 years if kept in a dry, cool store in the original, unopened packs. If stored at high temperatures and/or high humidity conditions, the shelf life may be reduced.

## HEALTH & SAFETY

Product safety information required for safe use is not included. Before handling, read product and safety data sheets and container labels for safe use, physical and health hazard information. The safety data sheet is available from your local **a.b.e.**® sales representative.

## IMPORTANT NOTE

This data sheet is issued as a guide to the use of the product(s) concerned. Whilst **a.b.e.**® endeavours to ensure that any advice, recommendation, specification or information is accurate and correct, the company cannot accept any liability for application – because **a.b.e.**® has no direct or continuous control over where and how **a.b.e.**® products are applied.

## FURTHER INFORMATION

Where other products are to be used in conjunction with this material, the relevant technical data sheets should be consulted to determine total requirements.

**a.b.e.**® has a wealth of technical and practical experience built up over the years in the company's pursuit of excellence in building and construction technology.

Please consult our website for our latest datasheets.

**abecote® 400 HB**  
**COLOUR CHART**

These colours are provided as a guidance only and exact colour matches will be dependent on the surface condition.



**AGATE GREY**



**BLACK**



**DIV GREY**




**DRAKENSBERG GREEN**



**FEDERAL MOGUL GREY**



**LEAF GREEN**



**LIGHT IVORY**



**LIGHT STONE**



**MED SEA GREY**




**PALE GREY**



**RED OXIDE**



**SAND YELLOW**



**WHITE**

DATE UPDATED: 12/10/2023

a.b.e.\* is an ISO 9001:2015 registered company  
Call: (+27) 860 223 773 | (+27) 11 306 9000  
[www.abe.co.za](http://www.abe.co.za)