



SAINT-GOBAIN

super laycryn[®]

**PROFESSIONAL LIQUID
WATERPROOFING
COMPOUND**



DESCRIPTION

super laycryn[®] is a highly flexible liquid applied emulsion reinforced with **abe[®] membrane** to provide an in situ, seamless professional waterproofing system.

USES

super laycryn is recommended for:

- All types of flashings
- Roof waterproofing: valley gutters and ridging
- Re-waterproofing over existing waterproofing systems
- Sealing of joints, laps and roofing screws on corrugated roofs
- The system is for non-trafficable roofs

ADVANTAGES

- **super laycryn[®]** is an all-in-one system
- There is no need for separate primers (apart from metal surfaces) or top coats
- It has excellent weathering properties, adhesion and is tough, flexible and non-toxic
- It comes in a wide range of colours
- 10 year product quality guarantee

COLOUR



SURFACE PREPARATION

All surfaces to be clean, dry, sound and free of all laitance, grease, oil or loose and flaking particles.

BONDING/PRIMING

All surfaces (except metal) – Mix 1 part **super laycryn[®]** with 1 part clean water and prime total area to be covered. As a guide, 0,1 litre of **super laycryn[®]** mixed with 0,1 litre of water will prime an area of 0,75 m².

Allow to dry for ± 30 minutes.

Metal surfaces only – Prime with 4 metal primer. This not only gives excellent adhesion but resists rust. Allow to dry for 4 hours.

NOTE: Do not use solvent based bituminous solutions as a primer.

TYPICAL PHYSICAL PROPERTIES

| | |
|-----------------------------|--|
| Density (typical) | 1.18 g/cm ³ |
| Flash point | None |
| Finish | Matt |
| Fire resistance of wet film | Non-flammable |
| Consistency | Soft thixotropic |
| Drying time @ 25 °C | Touch dry: 1 hour Hard dry: 24 hours Full cure: 7 days |

MIXING

Stir well before use.

COVERAGE

2,1 l/m² for total system.

APPLICATION

First coat (all surfaces after priming) - Brush or roll on a fairly thick coat of **super laycryn[®]** (1 litre/m²). Bed the membrane into the wet coat by using a roller or a stiff brush, avoiding the formation of bubbles or wrinkles. On flat

surfaces it is recommended to use a fluted aluminium roller. Membrane overlaps should be a minimum of 100 mm on end laps and 75 mm on side laps.

Second coat - Once the first coat has dried sufficiently to take working traffic (2 - 3 hours depending upon weather), apply a second coat of **super laycryn**[®] (0,5 litre/m²) to ensure the membrane is completely saturated.

Third and final coat - When the second coat is dry, apply a finishing coat of **super laycryn**[®] at right angles to the second coat (0,5 litre/m²).

CLEANING

Tools, brushes and mixing equipment should be cleaned immediately after use and before material has set with **abe**[®] **super brush cleaner** followed by washing with soap and water.

PROTECTION ON COMPLETION

Whilst **super laycryn**[®] is designed for an extended life, it is important to apply a maintenance coat of **super laycryn**[®] every 2 to 3 years to validate the product warrantee.

Note: Do not cover with stones or stone chippings.

TEMPERATURE AND RELATIVE HUMIDITY

Do not apply **super laycryn**[®] if rain is imminent or if the temperature is below 5 °C.

MODEL SPECIFICATION

Coloured acrylic and rubberised bitumen waterproofing flashing system plus **abe**[®] **membrane**. The waterproofing/flashing system will be **super laycryn**[®], a single-pack, elastic acrylic and rubberised bitumen compound applied in accordance with the recommendations of **a.b.e.**[®], including **abe**[®] **membrane** and 4 metal primer where necessary.

PACKAGING

1l, 5l, 20l containers.

HANDLING & STORAGE

This product has a shelf life of 12 months if kept in a dry cool place in the original packaging. In more extreme conditions this period might be shortened.

HEALTH & SAFETY

super laycryn[®] is non flammable but should not be allowed contact with skin and eyes. The use of gloves and eye protection is advised. Splashes into eyes should be washed immediately with plenty of clean water and medical advice sought thereafter. Cured **super laycryn**[®] is inert and harmless.

IMPORTANT NOTE

This data sheet is issued as a guide to the use of the product(s) concerned. Whilst **a.b.e.**[®] endeavours to ensure that any advice, recommendation, specification or information is accurate and correct, the company cannot accept any liability for application – because **a.b.e.**[®] has no direct or continuous control over where and how **a.b.e.**[®] products are applied.

FURTHER INFORMATION

- Where other products are to be used in conjunction with this material, the relevant technical data sheets should be consulted to determine total requirements.
- **a.b.e.**[®] has a wealth of technical and practical experience built up over the years in the company's pursuit of excellence in building and construction technology.
- Please consult our website for our latest datasheets.

DATE UPDATED: 25/10/2023

a.b.e.[®] is an ISO 9001:2015 registered company
Call: (+27) 860 223 773 | (+27) 11 306 9000
www.abe.co.za