



SAINT-GOBAIN

# brixéal

## BRICKWORK WATERPROOF COATING



### DESCRIPTION

**brixéal** is a bitumen emulsion waterproofer.

### USES

- **brixéal** is used for waterproofing the faces of concrete beams and pillars where they come into contact with exterior brickwork
- **brixéal** is used to prevent a bond developing between two adjoining concrete faces
- **brixéal** is used as a waterproof barrier between the two faces of a 230 mm thick wall. It is applied to the inner surface of the outer leaf, in stages, during construction
- **brixéal** is used as a concrete curing agent

**Note:** **brixéal** is black in colour

### ADVANTAGES

- Single pack ready to use
- Quick drying
- Economical

### SURFACE PREPARATION

All surfaces to be clean dry, sound and free of oils and laitance.

### BONDING/PRIMING

No special primer required.

### MIXING

Stir well before use.

### COVERAGE

Brushed coat on: 1<sup>st</sup> coat 2 m<sup>2</sup>/ℓ

Average unbagged: 2<sup>nd</sup> coat 4 m<sup>2</sup>/ℓ brickwork.

### TYPICAL PHYSICAL PROPERTIES

Flash point	None
Drying time @ 25 °C	Touch dry: ± 1 hour Hard dry: ± 12 hours Full cure: ± 7 days
Toxicity	Mildly caustic – avoid ingestion and prolonged skin contact
Colour	Black

### APPLICATION

Two coats of **brixéal** are recommended to ensure that any pinholes or lean spots left in the first coat are taken up, thus ensuring an even coating. Where brush applied, **brixéal** should be flowed on with as few strokes as possible, making sure that the surface is fully covered.

While **brixéal** may be applied directly to a stockbrick wall as a waterproof barrier, better results will be obtained if the surface is first 'bagged' with a sand/cement/water slurry in the usual way.

When **brixéal** is used for curing of concrete, a coating is brushed or sprayed onto the surface of the concrete, and by virtue of the waterproof qualities of the film, water is prevented from evaporating from the concrete. To allow traffic onto the concrete, the **brixéal** film can be blinded with clean sand after setting.

### CLEANING

Tools, brushes and mixing equipment should be cleaned immediately after use and before material has set with **abe® super brush cleaner** followed by washing with soap and water.

### TEMPERATURE AND RELATIVE HUMIDITY

Application temperature range: 5 °C to 40 °C

Do not apply if rain is imminent

### MODEL SPECIFICATION

Bituminous emulsion coating used as a waterproof barrier.

The waterproof coating will be **brixéal**, a bituminous emulsion applied in accordance with the recommendations of **a.b.e.®**

### PACKAGING

5 ℓ, 25 ℓ, 200 ℓ containers.

## HANDLING & STORAGE

This product has a shelf life of 12 months if kept in a dry cool place in the original packaging. In more extreme conditions this period might be shortened.

## HEALTH & SAFETY

**brixeal** is mildly caustic and should not be allowed contact with skin and eyes or ingested. The use of gloves and eye protection is advised. Splashes into eyes should be washed immediately with plenty of clean water and medical advice sought. Cured **brixeal** is inert and harmless.

## IMPORTANT NOTE

This data sheet is issued as a guide to the use of the product(s) concerned. Whilst **a.b.e.**® endeavours to ensure that any advice, recommendation, specification or information is accurate and correct, the company cannot accept any liability for application – because **a.b.e.**® has no direct or continuous control over where and how **a.b.e.**® products are applied.

## FURTHER INFORMATION

Where other products are to be used in conjunction with this material, the relevant technical data sheets should be consulted to determine total requirements.

**a.b.e.**® has a wealth of technical and practical experience built up over the years in the company's pursuit of excellence in building and construction technology.

Please consult our website for our latest datasheets.

DATE UPDATED: 25/03/2025

**a.b.e.**® is an ISO 9001:2015 registered company  
Call: (+27) 860 223 773 | (+27) 11 306 9000  
[www.abe.co.za](http://www.abe.co.za)